

REFERENCE TABLE

CROSS-SECTIONAL AREA AND MASS PER METRE

Diameter mm	CROSS-SECTIONAL AREA mm ²	MASS PER METRE kg/m
5	19.63	0.154
5.5	23.76	0.187
6	28.27	0.222
6.5	33.18	0.260
7	38.48	0.302
7.5	44.18	0.347
8	50.27	0.395
8.5	56.75	0.445
9	63.62	0.499
9.5	70.88	0.556
10	78.54	0.617
11	95.03	0.746
12	113.10	0.888
13	132.73	1.042
14	153.94	1.208
15	176.71	1.387
16	201.06	1.578
17	226.98	1.782
18	254.47	1.998
19	283.53	2.226
20	314.16	2.466
21	346.36	2.719
22	380.13	2.984
23	415.48	3.261
24	452.39	3.551

Diameter mm	CROSS-SECTIONAL AREA mm ²	MASS PER METRE kg/m
25	490.87	3.853
26	530.93	4.168
27	572.56	4.495
28	615.75	4.834
29	660.52	5.185
30	706.86	5.549
31	754.77	5.925
32	804.25	6.313
33	855.30	6.714
34	907.92	7.127
35	962.11	7.553
36	1017.88	7.990
37	1075.21	8.440
38	1134.11	8.903
39	1194.59	9.378
40	1256.64	9.865
41	1320.25	10.364
42	1385.44	10.876
43	1452.20	11.400
44	1520.53	11.936
45	1590.43	12.485
46	1661.90	13.046
47	1734.94	13.619
48	1809.56	14.205
49	1885.74	14.803